

# REZSTONE

2011 Seaman St., Toledo, Ohio 43605 **SPECIFICATIONS**

**9500-SD  
3/16" Static  
Dissipating Epoxy  
Floor Topping**

## 9500-SD 3/16" Static Dissipating Epoxy Floor Topping System

**Description:** Rez-Stone 9500-SD is a normal 3/16" epoxy based floor system which provides excellent static charge dissipating capabilities. Rez-Stone 9500-SD can be used where rapid strength gaining overlayment is required. When applied at 3/16 inch it is more impact, chemical, and wear-resistant than conventional floor systems. Typically recommended for economical leveling or resurfacing of concrete floor areas subjected to heavy industrial use, where static discharging is necessary.

**Advantages:**

- Economical
- Short downtime
- Excellent chemical, impact and abrasion resistance
- Non-slip finishes available
- Seamless cove base available
- Static dissipating

**Limitations:**

- Substrate minimum temperature 50°F.
- New concrete must be at least 28 days old.
- Do not apply over wet substrate.

### Coverage at Nominal 3/16" Thickness:

Prime Coat	175 - 225 Square Feet per Gallon	Rez-Stone 5014
Matrix Binder	35 Square Feet per Gallon	Rez-Stone 5014
Matrix Aggregate	1.5 Pounds per Square Foot	Blended Aggregate
(Optional) Grout Coat	90 Square Feet per Gallon	Rez-Stone 5017-C
Topcoat	90 Square Feet per Gallon	Rez-Stone 5078-C

## INSTALLATION

**Surface Preparation:** Concrete surfaces must be clean and sound. Remove all dust, laitance, grease, curing compounds and other bond inhibiting contaminants by shot blasting, scarification or other approved mechanical methods.

**Application:** After proper surface preparation, apply a prime coat using Rez-Stone 5014 Primer-Binder using a heavy-duty medium nap roller. Lightly broadcast, 1 pound per 5 square feet of blended aggregate into the wet primer to help trowel ability. (Note: Matrix may be placed immediately, but do not allow primer to cure for more than 24 hours before placement of overlay). Blend proportioned amounts of Rez-Stone 5014 Part A and Part B for 3 minutes using mechanical agitation. Load proportioned matrix aggregate into a paddle or screw-type mortar mixer followed by the pre-blended 5014 Binder. Mix for 1 minute. Place mixed material onto floor using a screed box or straight edge. Power-trowel the placed matrix for a smooth compacted finish. Allow matrix to cure for 8-10 hours or until tack-free. Once matrix has cured it should be lightly scraped with an ice spud or similar scraping tool and broom swept before topcoating. Install grounding cords if necessary to earth ground every 1,000 square feet before topcoating. Squeegee apply optional 5017-C grout coat depending on desired finish. Roller-apply Rez-Stone 5078-C 100% solids epoxy topcoat at a rate of 90 square feet per gallon for a lightly textured finish. If a non-slip finish is needed a silica or aluminum oxide aggregate may be incorporated into the topcoat.

## TYPICAL PROPERTIES AND SPECIFICATIONS OF CURED SYSTEM

Working Time .....	30-35 minutes @ 70°F
Cure Times: Initial Set-For-Life Traffic .....	16 hours @ 70°F
Ultimate Cure .....	7 days @ 70°F
Compressive Strength ASTM C-579 .....	10,500 psi
Tensile Strength ASTM C-307 .....	1,890 psi
Flexural Strength ASTM C-580 .....	4,500 psi
Shore "D" Hardness ASTM D-2240 .....	90
Water Absorption ASTM C-413 .....	0.2%
Percent Elongation ASTM D-638 .....	0.2
Abrasion Resistance ASTM D-4060 .....	0.1 gram
Moisture Vapor Permeability ASTM E96-80 .....	0.06 perms
Thermal Shock Resistance ASTM C-884 .....	Passes
Flammability ASTM D-635 .....	Self-extinguishing
Static Coefficient of Friction ASTM C-1028 .....	0.5 to 0.9 will vary with selected finish
Thermal Coefficient of Linear Expansion ASTM D-696 .....	$2.5 \times 10^{-5}$ in/in/deg F
Impact Resistance MIL-D-3134F .....	No Indentation
Bond Strength ACI Committee 403/59-43 .....	350 psi (100% concrete failure)
Electrical Resistance ASTM F-150-89 .....	0.25 - 25 mega ohms

---

**Safety Precautions:** Prolonged or repeated exposure to epoxy materials may cause eye or skin irritations. If contact occurs, wash affected area with soap and water immediately. If discomfort continues seek medical attention. Always wear suitable protective clothing and use proper safety devices. See respective MSDS for complete details.

---

**Clean-Up:** All tools and equipment should be cleaned before material gels. Use 1201 Epoxy Reducer or Xylene.

---

**Warranties:** Hoover & Wells warrants the quality of its Rez-Stone products, and takes responsibility only for furnishing specifications and recommendations for their proper installation. Hoover & Wells hereby disclaims all other warranties expressed or implied, and any implied warranties of merchantability or fitness for a particular purpose. Hoover & Wells shall have no liability to the Purchaser for any property damage, bodily injury, death, or other loss arising out of possession or use of Rez-Stone products. Hoover & Wells shall not be responsible for any claim resulting from failure to use its product other than the manner outlined with the instructions provided for use of the product. Under no circumstances shall Hoover & Wells be liable for any damages or otherwise in excess of the purchase price. Any claim for breach of warranty shall be given to Hoover & Wells in writing with 90 days of delivery or the claim shall be deemed waived. All information herein is provided in good faith only as an aid to the Purchaser. Thus, the Seller does not guarantee the accuracy of the information and assumes no liability for reliance thereon. Rez-Stone is a trademark of Hoover & Wells, Incorporated, Toledo, Ohio USA

2011 Seaman • Toledo, Ohio 43605 • (419) 693-1215